



## ACRYLIC FINE SWIRL T70256326F

### Product Description

Texturi Acrylic Fine Swirl is a textured acrylic polymer finish. It can be used to produce a fine "worm" finish.

### Features

- Durable finish
- Acrylic Based
- For masonry, stucco and concrete
- Easy water & soap clean-up

### Certification

- Not manufactured with lead, mercury or chromate containing materials
- Meets LEED and SCAMD product requirements for air quality
- Water vapor transmission (ASTM D1653 method B): 35 perms
- Moisture resistance (ASTM D2247): Passed
- Salt spray resistance (ASTM B117): Passed
- Accelerated weathering (ASTM G154): Passed
- Mildew resistance (ASTM D3273): Passed
- Flame spread (ASTM E840): FSI < 20, Class A
- Abrasion resistance (ASTM D968): Passed

### Technical Specifications

#### Solids

By Volume- 74% +/- 2%

#### Vehicle Type

Acrylic

#### VOC

<50 g/l

#### Weight per pail

65.0 lbs

#### Drying Time

- Dries within 24 hours

#### Coverage

125-135 sq. ft. / pail

### Application

Apply a uniform coat of Texturi Acrylic Fine Swirl, no thicker than the largest aggregate, to the substrate. The material is applied with a stainless steel trowel. Use a plastic float, with consistent pressure, in a figure eight motion to achieve the desired worm pattern effect. DO NOT use a jiffy-type mixer that exceeds 500 RPM to mix this product.

#### Drying

DO NOT apply product when the ambient surface temperature is below 40 F (4 C) or above 90 F (32 C). Protect all work from inclement weather with an approved system until cured. Drying time may vary due to climatic conditions. Ambient air and surface temperature must be above 40 F (4 C) during application and dry time.

Drying time may vary due to climatic conditions. Ambient air and surface temperature must be above 40 F (4 C) during application and dry time.

#### Primers

Primer is recommended over One Coat products, adhesive basecoats, brown coat, stucco, masonry, poured in place concrete and tilt up concrete to promote adhesion and uniform substrate for color consistency.

#### Curing

One coat stucco and masonry products must cure for a minimum of 7 days and concrete must be cured for a minimum of 28 days. The pH level of these products must be below 10 prior to application of the primer.

#### Surface Preparation

All surfaces must be clean, dry, firm and free of dirt, grease, oil, wax, and other contaminants.

#### Thinning & Clean-up

Product should be reduced, to achieve the viscosity desired, for application. Not to exceed 32 ounces per pail. If water is added, the same amount must be added to each pail to ensure color consistency. Clean with clean soapy water.

### Cautions

**WARNING!** DO NOT TAKE INTERNALLY. CLOSE CONTAINER AFTER EACH USE. KEEP OUT OF REACH OF CHILDREN

-Protect from freezing

**WARNING!** If you scrape, sand or remove old paint you may release lead dust. LEAD IS TOXIC, EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMAN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect you and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead)

### Warranty

Comex warrants that its products will conform and perform in accordance with the product specification sheet. Comex also warrants its products to be free from defects in material and manufacturing.



5575 DTC Parkway  
Suite 100  
Greenwood Village, CO 80111

Made in the U.S.A.

[www.thecomexgroup.com](http://www.thecomexgroup.com)

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications are subject to change without notice.

OCTOBER 2010

Page 1 of 1