



ACRYLIC EXTRAFINO INTERIOR T70258610F

Product Description

Texturi Acrylic Extrafino is a textured acrylic polymer finish. It can be used to produce a smooth or decorative "astrowealed" finish. The finish is very smooth and could be used to produce a "drywall-mud" like texture look on interior surfaces. Texturi Acrylic Extrafino can also be applied using texture pumps, hoppers, and some pneumatic equipment to produce an orange peel, splatter, or knockdown texture.

Features

- Acrylic Based
- Great Adhesion
- Extremely Durable and Hard
- Highly Permeable
- Easy water & soap clean-up

Certification

- Not manufactured with lead, mercury or chromate containing materials
- Meets LEED and SCAMD product requirements for air quality
- Water vapor transmission (ASTM D1653 method B): 66 perms
- Abrasion (ASTM D4060-C5-17 wheel 1 Kg tabor 1,000 cycles): Passed
- Salt spray resistance (ASTM B117): Passed
- Accelerated weathering (ASTM G154): Passed
- Mildew resistance (ASTM D3273): Passed
- Flame spread (ASTM E840): FSI <20, Class A
- Abrasion resistance (ASTM D969): Passed

Technical Specifications

Solids

By Volume- 57 ± 2%

Vehicle Type

Acrylic

VOC

<50 g/l

Weight per pail

60 lbs

Drying Time

- Dries within 24 hours

Coverage

Trowel Application: 120-300 sq ft per pail, depending on texture. Spray Application: 500-600 sq ft per pail. Coverage may vary due to application technique, ambient temperature, surface temperature, surface porosity, and/or application methods.

Application

Texturi Acrylic Extrafino Interior Texture Finish is the texture sprayed over Texturi Acrylic Surfacer, in a two-step system. This system creates an extremely durable, mildew resistant finish with a perm rating of 66. It is commonly applied as an orange peel, splatter, or knockdown finish, and can also be trowel applied for a variety of effects. Texturi Acrylic Extrafino Interior Finish, applied over Texturi Acrylic Surfacer, is recommended for use on interior walls and ceilings in hospitality and multi-family environments. The material can also be applied using a stainless steel trowel to create a variety of decorative finishes.

Drying

DO NOT apply product when the ambient surface temperature is below 40°F (4°C) or above 90°F (32°C). Protect all work from inclement weather with an approved system until cured. Drying time may vary due to climatic conditions. Ambient air and surface temperature must be above 40°F (4°C) during application and dry time.

Surface Preparation

Substrates are clean and free of loose material, dirt and dust, efflorescence, grease, oils, curing agents, and cleaning solutions. All surfaces must be smooth and free of irregularities. Repair all cracks with the appropriate patching material for the existing substrate. Painted or glossy surfaces must be dulled to promote adhesion.

Thinning & Clean-up

A small amount of water, not more than 16 ounces, may be added to each pail. If water is added, the same amount must be added to each pail to ensure color consistency. Clean with soapy water before drying.

Cautions

WARNING! DO NOT TAKE INTERNALLY. CLOSE CONTAINER AFTER EACH USE. KEEP OUT OF REACH OF CHILDREN

-Protect from freezing

Warning! If you scrape, sand or remove old paint you may release lead dust. LEAD IS TOXIC, EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMAN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect you and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Warranties

Comex warrants that its products will conform and perform in accordance with the product specification sheet. Comex also warrants its products to be free from defects in material and manufacturing.



5575 DTC Parkway
Suite 100
Greenwood Village, CO 80111

Made in the U.S.A.

www.thecomexgroup.com

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications are subject to change without notice.

OCTOBER 2010